

Formaldehyde Emission Summary – E0 MDF

REPORT NO. 08MDF-E0

Company Name:
The Laminex Group

Report Date:
26/6/08

Product Standard:
AS/NZS 1859.2:2004

Test Method:
AS/NZS 4266.16:2004

AS/NZS Limits:
≤0.5 mg/L

MR MDF		
Thickness	18	32
Result (mg/L)	0.26	0.25

STD MDF		
Thickness	18	25
Result (mg/L)	0.42	0.14

Testing completed and traceable to NATA certified laboratories

Authority:



Cameron Dellar
R&D Manager