

Formaldehyde Emission Summary – E1 MDF

REPORT NO. 08-MDF

Company Name:
The Laminex Group

Report Date:
26/6/08

Product Standard:
AS/NZS 1859.2:2004

Test Method:
AS/NZS 4266.16:2004

AS/NZS Limits:
≤1.0 mg/L

MR MDF						
Thickness	9	12	16	18	25	32
Result (mg/L)	0.74	0.76	0.63	0.55	0.46	0.51

STD MDF									
Thickness	3	6	7.5	9	12	16	18	25	32
Result (mg/L)	0.86	0.83	0.71	0.76	0.92	0.79	0.71	0.48	0.62

Testing completed and traceable to NATA certified laboratories

Authority:


Cameron Dellar
R&D Manager